ACIDIC RUTILE-ALUMINATYPE AGGLOMERATED SAW FLUX FOR HIGH SPEED WELDING

**ROFLX-81** 

GRAIN SIZE = 10X 60 BSS (0.25-1.60MM) AWS: SFA/A 5.17 F7AZ-EL8 ED SAW EN ISO 14174-A S RS 1 67 AC B.I. = 0.80

## **KEY FEATURES:**

ROFLX-81 is an agglomerated Acidic Aluminate Rutile-Silicate Type Flux specially designed for butt and Fillet welding with high speed welding. Excellent slag removal and exceptional bead finish.it is preferably used for welding thin plates at speeds higher then up to 2m/min. It provides good welding usability, easy slag removal, excellent anti-porosity property and beautiful bead appearance

## **APPLICATIONS**

- high speed beam welding process with twin wires
  general construction
- membrane wall panels, beam fabrications
  automotive etc

sheet fillet welding and single pass welding with both of sides

**RE-DRY CONDITION** 

• Re-drying recommended at 350°C for one hour before use.

MAIN CONSTITUTION(%)							
SiO2+TiO2	CaO+MgO	Al2O3+MnO	CaF2				
25	10	50	10				
CHEMICAL COMPOSITION:							

UNDER Wires	с	Mn	Si	S	Р
ROSUB-8	0.070	1.30	0.70	0.018	0.022
ROSUB-12K	0.095	1.40	0.75	0.018	0.020

## **MECHANICAL PROPERTIES**

UNDER Wires	YS (N/mm2)	UTS (N/mm2)	EL %	CHARPY "V" NOTCH IMPACT AT +20°C 0°C
ROSUB-8	400	510	26	L 09
ROSUB-12K	450	520	28	L 09

## WELDING POSITION



PACKING SPECIFICATION

PACKED IN POLYTHENE-LINE PAPER BAGS OF 25.00 KG NET WEIGHT.